



NOTES

1. PORTLAND CEMENT CONCRETE SHALL BE 4000 PSI (6 SACKS PER CUBIC YARD), 3/4" AGGREGATE.
2. THE PATTERN TO BE IMPRINTED SHALL MATCH "BOMANITE'S" BOMACRON RUNNING BOND BELGIAN BLOCK PATTERN.
3. THE COLOR HARDENER SHALL BE "BOMANITE'S" DESERT TAN OR QC CONSTRUCTION PRODUCTS DURANGO TAN OR APPROVED EQUIVALENT.
4. BOMANITE, MADERA, CA (209) 673-2411 OR QC CONSTRUCTION PRODUCTS, MADERA, CA (800) 452-8213.
5. THE COLOR HARDENER SHALL BE APPLIED EVENLY TO THE SURFACE OF FRESH CONCRETE BY DRY-SHAKE METHOD USING A MINIMUM OF 60 POUNDS PER 100 SQUARE FEET. IT SHALL BE APPLIED IN TWO MORE SHAKES, FLOATED AFTER EACH SHAKE AND TROWLED ONLY AFTER THE FINAL FLOATING.
6. WHILE CONCRETE IS STILL IN ITS PLASTIC STAGE OF SET, THE IMPRINTING TOOLS SHALL BE APPLIED TO THE SURFACE. THE SURFACE OF THE STAMPED CONCRETE SHALL THEN BE CURED AND SEALED PER MANUFACTURER'S (I.E. BOMANITE) RECOMMENDATIONS IMMEDIATELY AFTER COMPLETING THE IMPRINTING PROCESS.
7. CONTROL JOINTS SHALL BE PER CITY STD. S-4.

CITY OF NAPA

PUBLIC WORKS DEPARTMENT

STAMPED DECORATIVE CONCRETE
FOR MEDIANS

DRAWN BY:	BRL	CHECKED BY:	JGF
DATE:	06/2018	APPROVED BY:	JRL
SCALE:	NONE	DRAWING NO.	S-27
FIELD NOTES:			